

Product Selector Guide

Two Component Epoxy Systems for the Production of Moulds and Tools

HUNTSMAN

Enriching lives through innovation

Resin	Hardener	Mix ratio (pbw)	Colour	Density g/cm ³	Pot life (min.)*	Castable layer thickness (mm)	Applications	Temperature resistance after respective cure cycle °C (ISO 75)					
								50	100	150	200	250	
RenGel® Gelcoats													
SW 10	HY 2404	100 : 10	white	1,5	20	-	Working moulds (ceramic), negatives, models, jigs	60-80	easily machinable, polishable, low odour				
	HY 5159	100 : 8		1,5	60	-							
SW 419-1	HV 2419	100 : 13	black	2,3	15 - 20	-	Metalfforming tools, foundry patterns, general model making	60-70	high compressive strength, abrasion resistant				
SW 404	HY 2404	100 : 10	blue	1,8	15	-	Foundry patterns, copy-milling models, foaming moulds	80-100	abrasion resistant				
	HY 5159	100 : 8		1,8	50	-							
SW 18	HY 2404	100 : 20	green	1,3	10 - 15	-	Wet lay-up tools, vacuum forming tools	85-100	polishable, high chemical resistance				
	HY 5159	100 : 16		1,3	25	-							
SW 56	HY 2404	100 : 13	caramel	1,5	10 - 15	-	Pressure casting moulds (ceramic) wet lay-up tools	100-120	workable, polishable, chemical resistant				
	HY 5159	100 : 10		1,5	25 - 30	-							
XD 4615	HY 5159	100 : 15	black	1,3	25 - 30	-	Mould for composite tooling, vacuum forming tools	120-130	highly polishable, high chemical resistance				
SW 5200	HY 5211	100 : 20	black	1,6	18 hrs	-	Prepreg tools, high temperature tooling applications		high temperature				
	HY 5212	100 : 20	black	1,5	10 hrs	-							
	HY 5213	100 : 16	black	1,6	270	-							
RenGel® Coupling Coat													
P 99	HY 5159	100 : 11	grey	1,5	30	-	Coupling coat between gelcoat and backing	120	multipurpose coupling coat				
RenCast® Casting Systems													
CW 20	HY 49	100 : 5	blue	2	110	30	Foundry patterns, copy-milling models, metalfforming tools, foaming moulds	65-70	mineral filled, abrasion resistant				
CW 2418-1	HY 5160	100 : 15	black	2,3	120	80	Metalfforming tools, casting of dowel bushes, general model making, full & face casting, foundry patterns	50-65	metal filled, high compressive strength, cure: slow/medium/fast				
	HY 5161	100 : 15		2,3	60	20							
	HY 5162	100 : 15		2,3	30	10							
	HY 5118	100 : 20		2,2	80	40							
CW 2215	HY 5160	100 : 20	ivory	1,6	120	80	Suitable for a wide range of applications	50-65	easily machinable, colourable, cure: slow/medium/fast				
	HY 5161	100 : 20		1,6	45	20							
	HY 5162	100 : 20		1,6	25	10							
CW 5156-1	HY 5158	100 : 8	grey	1,6	80	80	Foam moulds, vacuum forming tools	130	chemical resistant, easily machinable				
CW 47	HY 33	100 : 15	grey	1,85	4.5 hrs	100	Prepreg tools, vacuum forming tools, injection moulds, high temperature tooling applications		castable up to 100mm, easily machinable			200-210	
RenLam® / Araldite® Laminating Systems													
CY 219	HY 5160	100 : 50	pale yellow	1,1	80	-	Laminates and backfilling with a variety of fillers	45-60	transparent, tack-free with adjustable reactivity, room temperature curing				
	HY 5161	100 : 50	pale yellow	1,1	40	-							
	HY5162	100 : 50	pale yellow	1,1	20	-							
M-1	HY 956	100 : 20	pale yellow	1,1	30	-	Laminates and backfilling with a variety of fillers	50	transparent, room temperature curing, good impregnation				
LY 113	HY 98	100 : 30	pale yellow	1,1	90 - 100	-	Low viscosity laminating system with good thermal properties	125	temperature resistant, excellent wetting out properties				
LY 5210	HY 5211	100 : 40	amber	1,1	24 hrs	-	Prepreg lay up tools, parts and structures, high temperature tooling applications		partial curing at room temperature, long pot life				
	HY 5212	100 : 40	amber	1,1	12 hrs	-							
	HY 5213	100 : 32	amber	1,1	180	-							
LY 8615	Aradur 8615	100 : 50	pale yellow	1,13	850 - 980	-	High temperature infusion system for composite tooling		high temperature, long pot life, low viscosity				
	XB 5173	100 : 38	pale yellow	1,14	300 - 400	-							
RenLam® Laminating Pastes													
LV 573-2	HY 2959	100 : 15	grey blue	1,1	45 - 60	20	Laminated shells and backing structures	50	up to 20mm layer thickness, hand applied				
LV 06	HY 06	100 : 15	grey blue	1,1	90	15	Laminated shells and backing structures	70	up to 15mm layer thickness, hand applied				
LV 10	HY 97 blue	100 : 20	grey blue	0,75	60	10	Light, stiff laminated shells and backing structures	125	light paste, hand applied				
RenPaste® Modeling Pastes													
SV 427-2	HV 427-1	100 : 100	brown	0,6	40	20	Models and patterns, general alteration or repair of models + patterns	50-55	room temperature curing, with other hardeners suitable for bonding RenShape® boards				
SV 36	HV 36	100 : 100	brown	0,5	60	40	Light models, patterns and repairs	50-55	no pin holes, light, easily machinable, hand applied, layer thickness 40 mm				

*gelcoats: 250ml, laminating resins: 50ml, casting systems and pastes: 1l

www.huntsman.com/advanced_materials
advanced_materials@huntsman.com

Huntsman Advanced Materials (Switzerland) GmbH

Klybeckstrasse 200, CH 4057 BASEL Tel: +41 61 299 11 11 Fax: +41 61 299 11 12

While all the information and recommendations in this publication are to the best of our knowledge, information and belief accurate at the date of publication, NOTHING HEREIN IS TO BE CONSTRUED AS A WARRANTY, EXPRESS OR OTHERWISE. IN ALL CASES, IT IS THE RESPONSIBILITY OF THE USER TO DETERMINE THE APPLICABILITY OF SUCH INFORMATION AND RECOMMENDATIONS AND THE SUITABILITY OF ANY PRODUCT FOR ITS OWN PARTICULAR PURPOSE. The sale of products referred to in this publication is subject to the general terms and conditions of sale of HUNTSMAN Advanced Materials (Europe) BVBA or its affiliated companies. All trademarks mentioned are either property of or licensed to Huntsman Corporation or an affiliate thereof in one or more, but not all, countries. © 2011 Huntsman Advanced Materials (Switzerland) GmbH.